
UREAFORMALDEHYDE RESIN- KFS WATER SOLUBLE

Number of revisions: 8
Date of last revision: 11.01.2016
Neochim PLC code: 19 - 03

General Information:

Appearance: Colourless homogeneous suspension with slightly yellowish shade without impurities

Use: impregnation of insulation surfaces

Specifications:

Indices	Typical Values	Limit Values
Dry residue at 100 ⁰ C, %	64.0	65.0 ± 3.0
Free formaldehyde, %	4.0	2.0 - 4.0
Viscosity at the moment of preparation at 20 ⁰ C, mPa.s	400	250 to 1800
pH of 50 % aqueous solution at 20 ⁰ C	8.0	7.5 – 8.5
Mixing of resin with water at 20 ⁰ C±1 ⁰ C, in 1:14 ration in the course of 8 hours	complete	complete
Density at 20 ⁰ C, g/cm ³	1.230	1.230 – 1.290

Packing:

Tank trucks and customer's packing

Date of issue: 07.05.1992

These data are based on our current knowledge, experience and technical equipment. They do not relieve customers of carrying out their own tests and experiments, due to the great diversity of possible effects in processing and application of our products. They do not imply any legally binding assurances of certain properties and applications. The recipients of our products ought to abide by the existing legislation and regulations as well as possible reserved rights.

Sales Director
e-mail: adimitrov@neochim.bg
Phone: + 359 391 60590
Fax: + 359 391 60595

Director Marketing, Analysis and Controlling
e-mail: sgrancharov@neochim.bg
Phone: +359 391 60580
Fax: + 359 391 60555