
**POLYAMIDE GLASS REINFORCED-
PAS 30**

Number of revisions : 8
Date of last revision: 13.01.2016
Neochim PLC code: 30-03

Information:

Appearance: natural colour granules /colouring is possible on client's request/

Use: manufacture of articles and details by injection moulding

Specifications:

Indices	Typical Values	Limit Values
Density at 20°C, kg/m ³	1.20 x 10 ³	min.1.20 x 10 ³
Glass fibres, %	28	30 ± 3
Moisture, %	0.2 - 0.3	max. 0.5
Mechanical impurities, %	0.001	max. 0.3

Packing:

* PE/Paper bags - 20 kg net

Date of issue: 07.05.1992

This data is based on our current knowledge, experience and technical equipment. It does not relieve customers to carry out their own tests and experiments; neither do they imply any legally binding assurance of certain properties and applications. The observation of existing legislation and proprietary rights is responsibility of those to whom we supply our products.

Sales Director
e-mail: adimitrov@neochim.bg
Phone: + 359 391 60590
Fax: + 359 391 60595

Director Marketing, Analysis and Controlling
e-mail: sgrancharov@neochim.bg
Phone: +359 391 60580
Fax: + 359 391 60555