

**POLYAMIDE ALKALINE - PAA
TYPE 1**

Number of revisions: 6
Date of last revision: 07.01.2015
Neochim PLC code: 31-01

Technical Information:

Appearance: block-bars

Application: as construction and anti-friction material for manufacturing of machinery parts as gear-wheels, bushings, bush-bearings, etc

Physicochemical Specifications:

Indices	Typical Values	Limit Values	Test method
Density at 20°C, kg/m ³	1.10 x 10 ³	min. 1.10 x 10 ³	350.31
Brinell hardness, MPa	120	min. 110	351.31
Martens heat resistance, °C	68	min. 65	352.31

Types of block-bars:

Ø, mm	30	35	45	60	75	95	115	145	165	175	220	300
h, mm	450	450	450	750	750	750	600	600	200	200	200	200

A, mm	440	110	110
B, mm	430	110	800
H, mm	95	800	800

On client's request, black-bars with other shapes and sizes could be manufactured.

Date of issue: 07.05.1992

This data is based on our current knowledge, experience and technical equipment. It does not relieve customers to carry out their own tests and experiments; neither do they imply any legally binding assurance of certain properties and applications. The observation of existing legislation and proprietary rights is responsibility of those to whom we supply our products.

Sales Director
e-mail: adimitrov@neochim.bg
Phone: + 359 391 60590
Fax: + 359 391 60595

Director Marketing, Analysis and Controlling
e-mail: sgrancharov@neochim.bg
Phone: +359 391 60580
Fax: + 359 391 60555